

Technical Data Sheet

Stainless Steel Fibre - 310

Stainless Steel Fibres reinforce concrete and refractories against thermal and mechanical shock and also against chemical reaction by reducing cracking, corrosive and spalling susceptibility. The fibres can be used in concrete and refractory operating conditions of :

- High thermal cycling
- Continuous fibre soaking temperature up to 1200°C in the refractory
- High mechanical shock
- High temperature corrosive atmospheres (sulphidation, chlorination etc.)
- Chemical corrosion in concrete

Product Specification

Base Material : Stainless Steel Wire
 Grade of Steel : AISI 310
 Fibre Type : Straight, Corrugated, Hooked-end
 Length (mm) : 6-60
 (other lengths available on request)
 Diameter (mm) : 0.30 - 0.60
 Chemical Composition (%) :

%C. Max.	%Mn. Max.	%Si. Max.	%S. Max.	%P. Max.	%Ni.	%Cr.
0.08	2.000	1.500	0.030	0.045	19-22	24-26

UTS N/mm² : 700 - 1800 (As per customer requirement)
 Surface : Bright / Matt
 Suitable for : All mixers, including high-intensity, Turbo, conventional and low-intensity Mixers and also suitable for sprayed concrete.

FIBREZONE

Tel. : 079 - 2640 4101
 Fax : 079 - 2644 0974
 E-mail : fibrezone2005@yahoo.com
 Web. : www.fibrezone.net